Product Highlights

- Working temperature -60°C to +250°C
- Good fluids
 resistance
- Easy to install
- Aesthetic solution
- Self amalgamating
- Local Protection

RubSilITS03/06.doc

Our manufacturing sites are certified ISO 9000, QS 9000 or ISO/TS 16949 and ISO 14001



Silicone Tape 66N-67N-68N 69N-78N-79N

The tapes 66N, 67N, 68N, 69N, 78N and 79N are silicone elastomer tapes which self-amalgamate at ambient temperature.

The minimum elongation for 66N and 67N is 300%.

Composed of an additional fiberglass base coated with selfamalgamating silicone elastomer, the tapes 68N, 69N, 78N and 79N provide a high temperature mechanical protection.

After several hours at ambient temperature, the surface of these tapes sticks together when a light pressure is engaged.

These tapes are used for the sealing, connecting and finishing the cut ends of sleeves exposed to high temperatures. These products could also be used to protect locally harness parts and connection accessories.



Performance Data

Silicone Tape 66N-67N-68N-78N-79N

| Droporty | Tests | Results | | | | | |
|--|---|-----------------|--------------|--------------|-------------|-------------|-------------|
| Property | | 66N | 67N | 68N | 69N | 78N | 79N |
| Working temperature | | -60°C to +250°C | | | | | |
| Elongation resistance | | 300% mini | 300% mini | 15% mini | 15% mini | 15% mini | 15% mini |
| Fluid resistance: Jet Fuel JP5 Hydraulic fluid Skydrol 500 B4 Mineral oil: NATO 0142 Synthetic oil: NATO 0156 Cleaning fluids MIL C 87936 25% Propanol + 75 % white spirit Forane 141 B Cooling fluid: MIL-A-8243 | Immersion in the fluids for few seconds of the silicone tape amalgamated on its support (Harness) | Ν | lo deteriora | ation to the | amalgama | ate tape | |

Product Specifications

| Description | Thickness | Width | Colour | Armed with glass tape | Packaging | NATO spec. |
|-------------------|-----------|-------|-----------|-----------------------------|-----------|------------------|
| Silicone Tape 66N | 0,3 mm | 19 mm | Red/Brown | No | 15 Rolls | 5970-14-467-8824 |
| Silicone Tape 67N | 0,5 mm | 19 mm | Black | No | 15 Rolls | 5970-14-474-7041 |
| Silicone Tape 68N | 0,3 mm | 19 mm | Red/Brown | Yes | 15 Rolls | 5970-14-464-7312 |
| Silicone Tape 69N | 0,5 mm | 19 mm | Black | Yes | 15 Rolls | - |
| Silicone Tape 78N | 0,5 mm | 25 mm | Red/Brown | Yes | 15 Rolls | - |
| Silicone Tape 79N | 0,5 mm | 25 mm | Black | Yes | 15 Rolls | - |

Recommendation time for perfect amalgamate

| Temperature (°C) | 250 | 200 | 150 | 127 | 120 |
|---|-----|-----|-----|-----|-----|
| Time for perfect self amalgamate (minute) | 15 | 20 | 35 | 80 | 120 |

Part Numbering System

| Example: | Description | Size | Colour | <u>Quantity</u> | |
|----------|-------------|-----------|----------|-----------------|--|
| | 66N | 19 x 15 m | Standard | 30 rolls | |

Availability

Bentley-Harris[®] Silicone Tapes are available in rolls of 15 meters.

Minimum quantity is 15 rolls.

Packaging includes a polyester separating film to prevent layers from sticking.



France/Compiègne Tel.: +33 (0) 3 44 30 39 00 Fax.: +33 (0) 3 44 30 39 49

The information and illustrations given herein are believed to be reliable. Federal-Mogul makes no warranties as to their accuracy or completeness and disclaims any liability in connection with their use. Federal-Mogul's only obligations are those in the standard term of sale for this product and Federal-Mogul will not be liable for any consequential or other damages arising out of the use or misuse of this product. Users should make their own evaluations to determine the suitability of the product for specific applications.

©1998 Federal-Mogul Systems Protection Group, manufacturer of Bentley-Harris protection products.